

**SIQ-AMIN 1203**

is a modified cycloaliphatic amine.

specification			
amine number	260	-	278 mg KOH/g
viscosity	0,3	-	0,45 Pa*s at 25 °C
color number		≤	4 Gardner scale

**SIQ-AMIN 1203**

is recommended for solvent free coatings and epoxy mortars with a high chemical resistance. A long pot-life combined with a fast curing is given.

technical data		
equivalent weight	115	g/EQ
specific weight	1,02	g/cm <sup>3</sup>
flash point	131	°C
storage stability	36	months
storage conditions	at a cool and dry place in sealed drum	

All recommendations for use of our products, wether given by us in writing, verbally, or to be implied from the results of tests carried out by us, are based on the current state of our knowledge. Notwithstanding any such recommendations the buyer shall remain responsible for satisfying himself that the product supplied by us are suitable for his intended process or purpose. Since we cannot control the application, use or processing of the products, we cannot accept responsibility therefore. We warrant that our products are free from defects in accordance with and subject to our general conditions of supply.