PROSTAR CHEMICALS CO., LTD.

20/36 Moo 3, Soi Jatuchot 4, Sukhapibal 5 Road,

Aunguen, Saimai, Bangkok 10220

Tel: (662)974-5605-8 Fax: (662)974-5609



SIQ-AMIN

2011

is a high viscosity polyaminoamide.

specification				dimension	test method
amine number	240	_	260	mg KOH/g	PM.01.001
viscosity	3,10	-	3,7	Pa*s at 75 °C	PM.01.003
color number		<	10	Gardner scale	PM.01.005

SIQ-AMIN

2011

is recommended for solvent based coatings and reactive adhesives.

THE W	LICATA
240 g/EQ 0,96 g/cm³ 500 - 1000 minutes >200 °C 36 months at a cool and dry place	in combination with SIQ-EPOX 4101
	0,96 g/cm³ 500 - 1000 minutes >200 °C 36 months

All recommendations for use of our products, wether given by us in writing, verbally, or to be implied from the results of tests carried out by us, are based on the current state of our knowledge. Notwithstanding any such recommendations the buyer shall remain responsible for satisfying himself that the product supplied by us are suitable for his intended process or purpose. Since we cannot control the application, use or processing of the products, we cannot accept responsibility therefore. We warrant that our products are free from defects in accordance with and subject to our general conditions of supply.