

PROSTAR CHEMICALS CO., LTD.

20/36 Moo 3, Soi Jatuchot 4, Sukhapibal 5 Road,

Aunguen, Saimai, Bangkok 10220

Tel : (662)974-5605-8 Fax : (662)974-5609

SERVICE · INNOVATION · QUALITÄT

S.I.Q.

S.I.Q.-KUNSTHARZE GMBH

EIQ-EPOX 4904

Glycidyl ether

specification		
epoxy value	3,10 - 3,50	Mole epoxide/kg
viscosity	0,005 - 0,010	Pa*s at 25 C
Color number		Max.1

EIQ-EPOX 4904

The reactive diluents are mainly used to reduce the high viscosity of epoxy resins based on bisphenol A and bisphenol F.

Technical data		
equivalent weight	303	g/EQ
specific weight	0.89	g/cm
flash point	155	C
storage stability	36	months
Storage condition at a cool and dry place in sealed drum		